

Aggregate Source Approval Report

Owner:	Aggregate Source: QS-N-148
Leasee:	Known as: Coal Creek Quarry
Located in: UNKNOWN Section 9,16, T8N R3W	County: Cowlitz

Remarks:

Pit Run Materials:

Prior to incorporating any of the following into a job, Gradation and Sand Equivalent tests shall be performed to determine if the material does in fact meet specification for the intended use:

Backfill for Rock Wall	Backfill for Sand Drains	Bedding Material for Rigid Pipe
Bedding Material for Thermoplastic Pipe	Blending Sand	Foundation Material for Classes A, B or C
Gravel Backfill for Drains and Drywells	Gravel Backfill for Foundation Class B	Gravel Backfill for Pipe Zone Bedding
Gravel Backfill for Walls	Gravel Borrow	Sand Drainage Blanket
Select or Common Borrow		

No Preliminary Tests are required to be performed by the State Materials Lab

Gravel Base:	Test Date:	Expiration Date:
Drainage:	R Value:	Swell Pressure:

Contact the Regional Materials Office to request PRELIMINARY SAMPLES be acquired. Evaluation and approval of this site as a source of GRAVEL BASE is required prior to use.

Mineral Agg. and Surfacing:

Absorption: 1.64	Apparent Sp. G.: 2.842	Bulk Sp. G. (SSD): 2.76	Bulk Sp. G.: 2.715
Deg: 89	LA: 24		

Currently approved as a source of aggregate for:

ATB	Ballast	BST Crushed Cover Stone
BST Crushed Screenings	Crushed Surfacing Base Course	Crushed Surfacing Key Stone
Crushed Surfacing Top Course	Gravel Backfill for Foundation Class A	HMA Other Courses
HMA Wearing Course	Maintenance Rock	Shoulder Ballast

Acceptance tests need to be performed as necessary.

Portland Cement Concrete Aggregates:	Test Date:	Expiration Date:
ASR - 14 Day:	ASR - One Year:	CCA Absorption:
FCA Absorption:	FCA Organics:	FCA Sp. G.:
Mortar Strength:	Petrographic Analysis:	CCA Sp.G.:
		LA:

Contact the Regional Materials Office to request PRELIMINARY SAMPLES be acquired. Evaluation and approval of this site as a source of AGGREGATES for PCC is required prior to use.

Riprap and Quarry Spalls:	Test Date: 08/31/2006	Expiration Date: 08/31/2007
Absorption: 1.64	Apparent Sp. G.: 2.842	Bulk Sp. G. (SSD): 2.76
Deg: 89	LA: 24	Bulk Sp. G.: 2.715

Contact the Regional Materials Office to request PRELIMINARY SAMPLES be acquired. Evaluation and approval of this site as a source of RIP RAP AND QUARRY SPALLS is required prior to use. **Aggregate Source Approval System**